

KRONO ORIGINAL PARQUET DESIGN

Level to use according to EN 13329:

Class 23 / 32 - AC 4

Domestic with heavy use

Commercial with general use



Dimension		
Dimension	thickness (d)	8,00 ± 0,50 mm dmax - dmin ≤ 0,50 mm
	length	1380 ± 0,50 mm dmax - dmin ≤ 0,50 mm
	width (b)	157,0 ± 0,10 mm bmax - bmin ≤ 0,10 mm
Structure		3D
Panels per box		10
Boxes per pallet		40
Tolerance		
Squareness	EN 13329	≤ 0,20 mm
Straightness	EN 13329	≤ 0,30 mm/m
Openings between elements	EN 13329	average: ≤ 0,15 mm max: ≤ 0,20 mm
Height difference between elements	EN 13329	average: ≤ 0,10 mm max: ≤ 0,15 mm
Test		
Resistance to water vapor	EN 438-2	≥ 3
Impact test	EN 13329	IC2
Stain resistance	Group 1 i 2	EN 13329 grade 5
	Group 3	EN 13329 ≥ grade 4
Sweeling after 24h	EN 13329	≤ 18 %
Scratch resistace	EN 438-2	≥ 3
Abrasion resistance	EN 13329	AC 4 (≥ 4000)
Environment		
Emission of Formaldehyde	EN 717-1	klasa E1

Made by: I. Mel

Strzelce Opolskie: 17.02.2012

Joanna Mel